Ultraleather — **Ultrafabrics**

291-5684 Arctic

291-0001 White

291-5805 Ermine

291-5714 Ice

291-5668 Silver Pearl

291-5666 Dove Grey

291-5040 Elephant

291-5708 Granite

291-5763 Charcoal

291-5806 Schooner

291-5607 Raven Wing

291-3720 Light Oyster

291-3455 Milkweed

291-3599 Almond

291-3700 Ivory

291-5250 Sassy

291-3601 Doe

291-3609 Buff

291-3850 Sand

291-3719 Champagne

291-8243 Apricot

291-5676 Pelican

291-3926 Cashmere

291-3851 Chamois

291-3778 Pecan

291-8233 Autumn Leaf

291-3729 Tan

291-3183 Pine Cone

291-1256 Papyrus

291-3612 Curry

291-1347 Poppy

291-3602 Stone

291-3523 Cave

291-3779 Taupe

291-3610 Hide

291-1176 Red

291-3777 Walnut

291-3666 Fudge

291-3205 Hot Chocolate

291-3469 Garnet

291-1311 Brick

291-7214 Boysenberry

291-2553 Cyan

291-2527 Lagoon

291-4430 Eucalyptus

291-5200 Citrus

291-1312 Chianti

291-2552 Riviera

291-2507 St. John

291-4314 Herbal Mist

291-4460 Parrot

291-6580 Sorbet

291-2508 Rain Dance

291-2685 Bayou

291-4351 Shetland

291-4454 Sonora

291-9385 Plum

291-2478 Diplomat Blue

291-2509 Poseidon

291-2551 Baltic

291-2556 Admiral

291-2555 Nile

Responsible Innovation

Ultraleather from Ultrafabrics

Application

Interior Upholstery

General Specifications

Composition:
100% Polycarbonate Polyurethane Surface
100% Reinforced Rayon Backing
containing TENCEL™ Modal fibers

Weight:
Approx. 9.7 oz. Per Square Yard
Approx. 330 Grams Per Square Metre

Thickness:
Approx. 0.95 Millimetres

Width:
54 Inches / 137 Centimetres

Repeat:
None

Performance

Abrasion:
ASTM D4157 / 400,000 Double Rubs (Wyzenbeek)*
BS EN ISO 12947-2 / 180,000 Rubs (Martindale)*
*meets or exceeds

Hydrolysis:
14+ Weeks
ASTM D3690 Sect. 6.11 (Hydrolytic Stability)
ISO 1419 Method C (Accelerated Ageing)

Adhesion of Coating:	ASTM D751
Tear Strength:	ASTM D2261
Breaking Strength:	ASTM D751
Tensile Strength:	BS EN ISO 1421

Colorfastness

Light:	AATCC 16.3, 200 Hours, Grade 4 ISO 105 B02, Grade 6
Crocking:	AATCC 8, Grade 4-5 Wet & Dry

Flammability Requirements

- ASTM E84 (Adhered) - Class A
- CA TB 117 - Pass
- FMVSS 302 & 95/28 Annex IV - Pass
- NFPA 260 - Class 1
- UFAC - Class 1

These fabrics, when treated and/or used with other compatible furniture components, have been shown to perform under the fire test conditions of:

- ASTM E84 (Unadhered)
- IMO FTPC Part 8
- BS EN 1021 Parts 1 & 2
- BS 5852 Source 0, 1 & 5 (Cig, Match & Crib 5)

For more information on certifications and standards, sustainability, as well as cleaning and care instructions, please visit our website.

INDOOR ADVANTAGE GOLD FURNITURE

2021-2022 SUSTAINABILITY LEADER MINDCLICK

La-Z-Boy Healthcare | KNÜ

ultrafabricsinc.com

TENCEL™ is a trademark of Lenzing AG

Ultrafabrics® and logo, and Ultraleather® are registered trademarks of Ultrafabrics Inc. Made in Japan.